

# Technical Information





## RAX0695

### RAXON PR10 ANTISCRATCH CLEAR

### HS 5LT

- Easy and safe to spray, fast drying, easy to polish
- To be used on 1 or 2 vertical panels
- Multi colored paint jobs, signwriting and plastic parts

## Application

	Mixing Ratio	100 % by volume	RAX0695
		50 % by volume	RAX0678
	2:1+10 %	10%	THINNER
	Spray viscosity at 20°C	DIN 4: 16 s	
	Potlife at 20°C	4 h	
	HVLP spray gun		
	Nozzle size	1.3 mm	
	Application pressure	2 bar	
	Nozzle pressure	0.7 bar	
	Compliant gravity-feed spray gun		
	Nozzle Size	1.3-1.4 mm	
	Application Pressure	2 bar	
	Number of spraycoats	2 - 3	
	Film thickness	50-60 µm	

### Safety advice:

The products are suitable for professional use only.  
 It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



# Technical Information

## RAX0695

RAXON PR10 ANTISCRATCH CLEAR

HS 5LT

Drying

	Drying at 20 °C	4 h dust-free: 2 h
	Drying at 60 °C	10/15 min
	Infrared (short wave)	8 min
	Infrared (medium wave)	10-15 min

### Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.