

Technical Information

RAX0700

RAXON UC30 UNIVERSAL






ANTISCRATCH CLEAR

HS clearcoat for high quality

Clear for baslac basecoat 35-

- ◆ High solids content, excellent weathering resistance
- ◆ Good polishing behaviour
- ◆ High gloss, high finish quality

Application

	Mixing Ratio 2:1+10 %	100 % by volume 50 % by volume 10 % by volume	RAX0700 50-20, -30 60-10, -20, -30, -40
	Spray viscosity at 20°C		DIN 4: 18-20 s
	Potlife at 20°C		4 h
	HVLP spray gun		
	Nozzle size		1.3 mm
	Application pressure		2 bar
	Nozzle pressure		0.7 bar
	Compliant gravity-feed spray gun		
	Nozzle Size		1.3-1.4 mm
	Application Pressure		2 bar
	Number of spray coats		2
	Film thickness		50-70 µm
	Flash off at 20°C		2-3 min after each spray coat

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.



Technical Information

RAX0700

RAXON UC30 UNIVERSAL

ANTISCRATCH CLEAR

Drying

	Drying at 20°C	8 h
	Drying at 60°C	30 min
	Infrared (short wave)	8 min
	Infrared (medium wave)	10-15 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.